





BETF-341/076-14-eng cancels and replaces BETF-341/343-13-eng

# SOPRASPRAY

**SOPRASPRAY** is a ready-to-use quick-drying adhesive primer composed of bitumen and volatile solvents.

Application	
	good adhesion of the bituminous products. It provides excellent nes, metals, insulation boards, wood, concrete, brick and hard styrene should be avoided.
Composition	
Bitumen, solvents and propellants.	
Packing	
500 ml spray can. Store in a cool dry plac sunlight. Shelf life: 12 months in unopene	ce, at temperatures between $+10~^{\circ}\text{C}$ and $+30~^{\circ}\text{C}$ , out of direct ed original packaging.
Characteristics	

	SOPRASPRAY
Colour	black
Dry residue (%) (indicative value)	30 - 35
Specific weight at 20°C (kg/l) (indicative value)	0,77 - 0,81
Drying time * (indicative value)	± 30 min.
Consumption (I/m²) (indicative value)	± 0,25

<sup>\*</sup> Depending on the temperature, the relative humidity and the layer thickness.

### Installation

Shake can well for about 2 minutes before use. Install at a temperature of at least 10 °C. Provide good protection on areas which do not require treatment. The surface must be clean, dry and free of dust and grease. Spray from approximately a 30 cm distance, in an even layer directly onto the surface to be treated. Keep the can upside down and keep spraying for about three seconds after use. This will prevent blockage of the valve. Clean tools with turpentine or white spirit. Hardened material can only be removed mechanically.

SOPREMA NV reserves the right to amend the composition of its material and consequently their prices, without prior notice. For this reason, all orders will be accepted only in accordance with the conditions and technical specifications in force at the date of order.





# **TECHNICAL DATASHEET**



BETF-341/076-14-eng cancels and replaces BETF-341/343-13-eng

## **Special indications**

#### **Health and Environment:**

The product does not contain any substance which is likely to be detrimental to health or to environment and complies with generally admitted Health and Safety Requirements. For more detailed information, please refer to the relevant safety data sheet.

#### Quality control:

**SOPREMA** has always attached the highest importance to Quality Control. For this reason, we operate an independently monitored Quality Assurance System in line with **EN ISO 9001:2008** and **EN ISO 14001:2004**.



Marnix DERKS
Technical Director

SOPREMA NV reserves the right to amend the composition of its material and consequently their prices, without prior notice. For this reason, all orders will be accepted only in accordance with the conditions and technical specifications in force at the date of order.